

ICC-ES Evaluation Report

ESR-5192

Issued November 2024

Subject to renewal November 2025

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2024 ICC Evaluation Service, LLC. All rights reserved.

<p>DIVISION: 06 00 00 – WOOD, PLASTICS AND COMPOSITES</p> <p>Section: 06 16 23 – Subflooring</p>	<p>REPORT HOLDER:</p> <p>NEXGEN BUILDING PRODUCTS LLC</p> 	<p>EVALUATION SUBJECT:</p> <p>MAXTERRA™ MgO FIRE- AND WATER-RESISTANT BACKER BOARD AND UNDERLAYMENT PANELS</p>	
--	---	--	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2021, 2018 and 2015 [International Building Code® \(IBC\)](#)
- 2021, 2018 and 2015 [International Residential Code® \(IRC\)](#)

Property evaluated:

- Durability
- Surface Burning Characteristics
- Structural

2.0 USES

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels are intended for use as floor underlayment or as tile backer board on walls and floors. The products are intended for use in Type V construction under the IBC and all construction types under the IRC.

3.0 DESCRIPTION

3.1 General:

3.1.1 MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board Panels are nominal ¼-inch (6 mm), ⅜-inch (9 mm), ½-inch (12 mm), and ⅝-inch (16 mm) thick magnesium-oxide panels reinforced with multiple embedded fiberglass mesh sheets. The MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels are available in nominal 4-foot (1.22 m) widths at a nominal length of 8 feet (2.44 m) or nominal 3-foot (0.914 m) widths at a nominal length of 5 feet (1.52 m). The panels are available with square edges or tapered edges along the length of the panels.

3.2 Surface Burning Characteristics:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels exhibit a flame spread index of 0 and a smoke developed index of 0 when tested in accordance with ASTM E84. The panels exhibit a Class A interior finish in accordance with Section 803.1.2 of the 2021 and 2018 IBC (Section 803.1.1 of the 2015 IBC).

4.0 DESIGN AND INSTALLATION

4.1 Design:

4.1.1 Use as Underlayment:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels may be used as floor underlayment on top of a structural subfloor system constructed to meet the applicable building code requirements; see section 4.2.1 and [Tables 1](#) and [2](#).

4.1.2 Use as Backer Board on Walls:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels may be directly attached to wall studs in accordance with Section 4.2.2 and [Table 3](#). The panels are suitable for use with ceramic tile, natural stone or dimensional stone veneers on walls in interior dry areas.

4.2 Installation:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels must be installed in accordance with the manufacturer's published installation instructions and this report.

4.2.1 Underlayment:

4.2.1.1 General:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board Underlayment Panels must be fully supported by a structural floor system, such as those described in [ESR-5194](#) utilizing MAXTERRA™ Non-Combustible Single-Layer Structural Floor Panels or conventional wood structural panels designed and installed in accordance with the applicable codes. For all installations, the structural floor system must be designed to limit the deflection, including live and dead loads, to L/360 of the span, in accordance with the applicable code. Any flatness or surface quality requirements of the structural subflooring must be addressed prior to installing the MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels.

Board joints must be in moderate contact, in a staggered brick pattern. MAXTERRA™ MgO Fire- and Water-Resistant Underlayment Panel edges must be staggered from subfloor joints, and four corners of the backer board sheets must not meet at one point. Additionally, joints in the panels must be provided where existing structural joints (such as building control joints) occur and where changes in direction occur, such as in L-shaped rooms. Underlayment edges must be kept $\frac{1}{8}$ inch (3.2 mm) away from rigid structures such as walls and cabinet bases, and cut edges of underlayment must face towards the outside (toward the wall / cabinet base / other rigid structure), as applicable. Installation must be in accordance with the manufacturer's installation instructions and the applicable codes. Fastening must be in accordance with [Table 1](#) of this report when used with floor finishes other than tile. For use with tile finishes, follow instructions in Section 4.2.1.2 and the fastening schedule in [Table 2](#) of this report.

4.2.1.2 Use as underlayment with tile floor finishes:

For tile applications, MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels [$\frac{3}{8}$ -inch (9 mm), $\frac{1}{2}$ -inch (12 mm), and $\frac{5}{8}$ -inch (16 mm) thick] must be installed in accordance with the underlayment instructions outlined in Section 4.2.1.1 and the applicable provisions of ANSI A108.11. For large, tiled areas, joints must be provided in accordance with ANSI A108.01, as applicable. The backer board must be adhered to the subfloor with mortar in accordance with ANSI A108.11. Fastening must be in accordance with [Table 2](#) of this report.

4.2.2 Backer Board (Walls)

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels must be installed in accordance with the fastening schedule shown in [Table 3](#) of this report and the applicable provisions of ANSI A108.11. When installed in accordance with [Table 3](#) of this report, the minimum interior uniform load requirement of 5 psf outlined in Section 1607.16 of the 2021 IBC (Section 1607.15 of the 2018 IBC and Section 1607.14 of the 2015 IBC) as well as the deflection limit of L/360 outlined in Table 1604.3 of the IBC and Table R301.7 of the IRC have been considered. Backer boards installed on walls must be placed with a minimum $\frac{1}{4}$ -inch (6.4 mm) clearance from floor surfaces and other horizontal tile termination locations. The gap must be free from adhesives or mortar and must be filled with a flexible sealant. For large, tiled areas, joints must be provided in accordance with ANSI A108.01, as applicable.

4.2.3 Finishes:

4.2.3.1 Floor Finishes When Used as Underlayment:

Flooring systems, such as carpet or resilient flooring, installed on MAXTERRA™ MgO Fire- and Water- Resistant Backer Board Underlayment Panels must be installed in accordance with the flooring manufacturer's published installation instructions. For tile finishes, see Section 4.2.3.2.1 of this report.

4.2.3.2 Finishes When Used as Backer Board:

MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels used as interior substrate sheets may be decorated with paint, wallpaper, ceramic tile, natural stone or dimensional stone veneers on walls in interior dry areas.

4.2.3.2.1 Tile, Natural Stone, and Dimensional Stone Veneer Installations:

For tile, natural stone and dimensional stone veneers, only those that are compatible with dry-set Portland cement mortars complying with ANSI A118.1 or latex modified thin set mortars complying with ANSI A118.4 may be used. Prior to setting the covering, all panel joints must be filled with the same mortar used to set the covering. Spread the mortar until it extends approximately 1-1/2 inches (38.1 mm) on each side of the joint. While the mortar is still wet, 2 inch-wide (51 mm), high strength, coated, alkali resistant, glass fiber reinforcing tape must be embedded into the wet mortar prior to applying the mortar to the field of the panel and subsequent tile covering materials.

4.2.3.2.2 Use with Paint or Wallpaper:

A flush-joint procedure must be used on the panels. Gypsum board joint compounds complying with ASTM C474 and C475 must be troweled into the joints. Paper joint tape must be embedded into the wet joint compound and allowed to thoroughly dry. Additional coatings of joint compound over the joint tape must be applied as needed to acquire the desired level of finish. Fastener heads in the field of the panels must also be covered with joint compound. Once the panels have been finished to the desired level, primer and paint or wallpaper may be applied in accordance with the primer and paint or wallpaper manufacturer's instructions.

5.0 CONDITIONS OF USE:

- 5.1 MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels must be installed in accordance with this report and the manufacturer's published installation instructions. In the event of a conflict between this report and the manufacturer's published installation instructions, this report governs.
- 5.2 For use as underlayment, the structural must be designed for a maximum allowable assembly deflection of L/360 for the applicable design loads.
- 5.3 Compatibility of resilient flooring and any applicable adhesives is outside of the scope of this report.
- 5.4 Compatibility of organic adhesives is outside of the scope of this report.
- 5.5 Use of MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels in fire-resistance rated construction is outside of the scope of this report.
- 5.6 Use of MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels to resist in-plane racking shear loads or horizontal diaphragm loads is outside of the scope of this report.
- 5.7 Compatibility of resilient flooring, primer, paint, and wallpaper / wallpaper adhesive with the panels is outside of the scope of this report.
- 5.8 MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels are limited to use on interior surfaces as defined in 2021, 2018 and 2015 IBC Section 202. The panels must not be used in wet areas as defined in IBC Section 2509; under the IRC, the panels must not be used in showers.
- 5.9 MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels are manufactured under a quality-control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Fiber-reinforced Magnesium-oxide-based Sheets \(AC386\)](#), dated October 2023.

- 6.2 Data in accordance with applicable sections of the [ICC-ES Acceptance Criteria for Reinforced Cementitious Sheathing and Floor Underlayment \(AC376\)](#), dated August 2012 (editorially revised January 2021).
- 6.3 Data in accordance with applicable sections of the [ICC-ES Acceptance Criteria for Fiber-Cement Interior Substrate Sheets Used in Wet and Dry Areas \(AC378\)](#), dated August 2012 (editorially revised January 2021).

7.0 IDENTIFICATION

- 7.1 The ICC-ES mark of conformity, electronic labeling, or the evaluation report number (ICC-ES ESR-5192) along with the product name (MAXTERRA™ MgO Fire- and Water- Resistant Backer Board and Underlayment Panels), registered trademark, or registered logo of the report holder must be included in the product label.
- 7.2 The report holder’s contact information is the following:

NEXGEN BUILDING PRODUCTS LLC
1904 MANTEE AVE WEST #300
BRADENTON, FL 34205
(727) 620-3334
www.nexgenbp.com
support@nexgenbp.com

TABLE 1 – FLOOR UNDERLAYMENT FASTENER CONFIGURATIONS (Non-Tile Applications)

Panel Thickness	Fastener Type ^{1,2}	Perimeter Spacing ³	Field Spacing
1/4" (6 mm) 3/8" (9 mm)	1/4" crown chisel point staple ⁴	2-inches O.C.	4-inches O.C.
	3d (.083-in. dia.) x 1-1/4 in. ring shank nails		
1/2" (12 mm) 5/8" (16 mm)	0.113-in. dia. x 1-1/2 in. to 2 in. ring shank nails	6-inches O.C.	12-inches O.C.
	#8 x 1-1/2 in. to 2 in. wafer head screws		

For SI: 1 inch =25.4 mm

¹Fasteners must be corrosion resistant (electrogalvanized, hot-dipped galvanized, or stainless).

²Fasteners must be set flush or just below panel surface.

³Fasteners must be placed a minimum of 1/2-inch from edges and 2-inches from corners.

⁴Staple length must be selected such that it embeds at least 85% of the thickness of the subfloor but does not protrude from the bottom of the subfloor panel.

For example: 1" length staples should be used with 1/4-inch thick underlayment and 3/4-inch thick subfloor; 7/8" length staples should be used with 1/4-inch thick underlayment and 5/8-inch thick subfloor.

TABLE 2 – FLOOR UNDERLAYMENT FASTENER CONFIGURATIONS (Tile Applications)^{4,5}

Panel Thickness	Fastener Type ^{1,2}	Perimeter Spacing ³	Field Spacing
3/8" (9 mm) 1/2" (12 mm) 5/8" (16 mm)	0.113-in. dia. x 1-1/2 in. to 2 in. ring shank nails	8-inches O.C.	8-inches O.C.
	#8 x 1-1/2 in. to 2 in. wafer head screws		

For SI: 1 inch =25.4 mm

¹Fasteners must be corrosion resistant (electrogalvanized, hot-dipped galvanized, or stainless).

²Fasteners must be set flush or just below panel surface.

³Fasteners must be placed a minimum of 1/2-inch from edges and 2-inches from corners.

⁴Underlayment must be adhered to subfloor with mortar in accordance with ANSI A108.11.

⁵Joints must be filled with mortar and 2 inch-wide (51 mm), high strength, coated, alkali resistant, glass fiber reinforcing tape must be embedded into the wet mortar

TABLE 3 – BACKER BOARD FASTENER CONFIGURATIONS (Walls)

Panel Thickness	Framing and Fastening Requirements for Wall Applications ⁵				
	Framing Type	Framing Spacing	Fastener Type	Perimeter Spacing	Field Spacing
1/4" (6 mm)	Minimum 2 x 4 lumber	16-inches O.C.	11 ga x 3/8 in. Head Diameter Roofing Nails ³ -Or- # 8-18 x 3/8 in. Head Diameter ribbed wafer head screws ³	8" O.C.	8" O.C.
3/8" (9 mm)					
1/2" (12 mm)					
5/8" (16 mm)					
1/4" (6 mm)	Cold-Formed Steel ²	16-inches O.C.	# 8-18 x 3/8 in. Head Diameter ribbed wafer head screws ⁴	8" O.C.	8" O.C.
3/8" (9 mm)					
1/2" (12 mm)					
5/8" (16 mm)					
1/4" (6 mm)	Minimum 2 x 4 lumber ¹	24-inches O.C.	Grabber GCB8158HL	6" O.C.	12" O.C.
3/8" (9 mm)					
1/2" (12 mm)					
5/8" (16 mm)					

For SI: 1 inch =25.4 mm, 1 psf = 47.88 Pa

¹ Minimum Specific Gravity of 0.55.

² Minimum 20 gauge (0.33 in.) thick ASTM A653 G60 galvanized. Minimum depth of 3-1/2 in. for residential applications or 3-5/8 in. for commercial applications.

³ Fastener must be corrosion resistant (electrogalvanized, hot-dipped galvanized, or stainless) and of sufficient length to achieve minimum embedment depth in to stud of 3/4-inch.

⁴ Fastener must be corrosion resistant (electrogalvanized, hot-dipped galvanized, or stainless) and of sufficient length to achieve minimum embedment depth in to stud of 1/4-inch.

⁵ The panels are not to be used for ceiling application.